

CEMENT ALL™

HIGH STRENGTH NON-SHRINK GROUT



SUMMARY OF PROPERTIES

All tests were carried out at 21°C until the age of the test. Tests were carried out at a water addition rate of 3.6L per 25kg.

Notes: All test results are independent third party results. Results for Compressive strength based on 70mm cube samples. The test results listed are derived from laboratory testing. Results will vary if standard sample sizes or test conditions vary. Refer to Technical Data Sheets for application and installation instructions.

COLOUR

Light Grey (when dry)

YIELD @ 21°C

0.014m³ per 25 kg bag

APPLICATION THICKNESS

0 – 100mm

PACKAGING

25kg Bags

50 Bags per pallet

SETTING TIME

ASTM C191

Initial: 15 Minutes

Final: 1 Hour

Compressive Strength

ASTM C109 Mod

Typical Result

1 hour	20.7MPa
3 hours	31.0MPa
7 Days	41.4MPa
28 Days	62.0MPa

Flexural Strength (Modulus of Rupture)

ASTM C78

Typical Result

7 Days	7.4MPa
28 Days	7.5MPa

Tensile Strength

ASTM C496 - Splitting Tensile

Typical Result

7 Days	6.0MPa
28 Days	7.5MPa

Modulus of Elasticity

ASTM C469 - Static Modulus of Elasticity

Typical Result

7 Days	3.34 x 10 ⁴ MPa
28 Days	3.82 x 10 ⁴ MPa

Dimensional Change

ASTM C157

Typical Result

In Air at 28 days	-0.051%
In Water at 28 days	-0.051%

Coefficient of Thermal Expansion

ASTM C531

2.53 x 10⁻⁶ / °C

Fresh Wet Density

ASTM C138

2129 kg/m³

Bond Strength

ASTM C882 Mod - By Slant Shear

Typical Result

1 day	9.7MPa
28 days	17.9MPa