WUNDERFIXX™

HIGH PERFORMANCEGREY CONCRETE SMOOTHING COMPOUND

Highlights

Easy to use – just add water.

Ultra smooth finish – grit free and sandable in 1 hour from final set.

Self-Curing technology – no water required under normal conditions.

Water resistant – durable in wet conditions

Interior and exterior use

Compressive Strength

ASTM C109 Mod

Typical Result

24 hours	7.0 MPa
28 Days	14.0 MPa

SUMMARY OF PROPERTIES

All tests were carried out at 21˚C until the age of the test. Tests were carried out at a water addition rate of 3.6L per 25kg.
Notes: All test results are independent third-party results. Results for Compressive strength based on 70mm cube samples. The test results listed are derived from laboratory testing. Results will vary if standard sample sizes or test conditions vary. Refer to Technical Data Sheets for application and installation instructions.

COLOUR (when dry)
Approximate grey of Portland Cement

YIELD @ 21 ˚C
0.014m³ per 22.7 kg bag

APPLICATION THICKNESS
Skim Coat to 13mm

PACKAGING
22.7kg Bags
52 Bags per pallet

SETTING TIME (pending conditions)
Initial: 15 Minutes
Final: 1 Hour

19-21 Cann Street, Guildford, NSW 2161
02 8376 4412 | info@antoun.com.au
antoun.com.au